
# **DATA SHEET**

Product Number: 110-43-328-41-001000



Description:
DIP Socket
Solder Tail
Standard Solder Tail (0.125 Tail)
Open Frame
Through Hole
Accepts .015-.025" Leads
Plating Code:
43
Shell Plating:
200 μ" Tin (matte finish) over 100

μ" Nickel

Inner Contact Plating:
30 μ" Gold over 50 μ" Nickel

Packaging: Packaged in Tubes

# Of Pins	A	В	С	Qty. per Tube	Mill-Max Part Number	RoHS Compliant
28	1.4	0.3	0.4	14	110-43-328-41-001000	RoHS 2002/96/EC

## **CONTACT:**

Contact Used: #30, Standard 4 Finger Contact

Current Rating = 3 Amps


**BERYLLIUM COPPER ALLOY** 172 (UNS C17200) per ASTM B 194

# **Properties of BERYLLIUM COPPER:**

- Chemical composition: Cu 98.1%, Be 1.9%
- Temper as stamped: TD01

Properties after heat treatment (TH01):

- Hardness: 36-43 Rockwell C
- Mechanical Life: 100 Cycles Min.
- Density: .298 lbs/in3
- Electrical Conductivity: 22% IACS\*
- Resistance: 10 miliohms Max
- Operating Temperature: -55°C/+125°C
- Melting point: 980°C/865°C (liquidus/solidus)
- Stress Relaxation†: 96% of stress remains after 1,000 hours @ 100 °C; 70% of stress remains after 1,000 hours @ 200 °C



<sup>\*</sup>International Annealed Copper Standard, i.e. as a % of pure copper.

†Since BeCu loses its spring properties over time at high temperatures; it is rated for continuous use up to 150°C. For applications up to 300°C, Mill-Max offers many contacts in Beryllium Nickel. Contact Tech Support for more info.

#### LOOSE PIN:

Pin Used: 1001 (Brass Alloy)

# BRASS ALLOY (UNS C36000) per ASTM B 16

## **Properties of BRASS ALLOY:**

- Chemical composition: Cu 61.5%, Zn 35.4%, Pb 3.1%†
- Hardness as machined: 80-90 Rockwell B
- Density: .307 lbs/in3
- Electrical conductivity: 26% IACS\*
- Melting point: 900°C/885°C (liquidus/solidus)

 $\pm$ (3 to 4% lead is used to permit "free machining" and is permitted by EC Directive 2002/95Annex 6; so all pin materials are RoHS compliant)

\*International Annealed Copper Standard, i.e. as a % of pure copper.

## **INSULATOR INFORMATION:**

PCT Polyester, (Thermx CG933, black)

High Temperature

## **Properties of PCT Polyester:**

- Brand: Thermx
   Grade: GG 022
- Grade: CG-933
- Rated voltage: 100 VRMS/150 VDC
- Insulation resistance: 10,000 Megaohms min.
- Material Heat Deflection Temp (per ASTM D 648): 529°F (276°C) @ 66 psi
- Dielectric strength: 1000 VRMS min. (700 VRMS min. for series 117 Shrink DIP)

Note: Materials above  $446^{\circ}F$  (230°C) are considered suitable for "eutectic" reflow soldering, above  $500^{\circ}F$  (260°C) for "lead-free" reflow soldering.